AGG SEALER 888

CATALINA CHEMICAL

PRODUCT DATA SHEET

PRODUCT DESCRIPTION

AGG Sealer 888 is a solvent based, high gloss, acrylic sealer. Formulated to efficiently seal rough or porous surfaces, preventing moisture and dirt from penetrating the surface. Designed to resist fading or discoloring, and maintain a gloss/wet look for long periods of time. Use when a **high gloss or wet look** is desired. For interior or exterior use.



RECOMMENDED SURFACES

- Mexican Saltillo
- Concrete
- Brick
- Stone
- Unglazed Tile
- Exposed Aggregate
- Deep Cut Brick Pavers
- Any porous surface where a high gloss is desired

COVERAGE

Allow 24 hours between coats.

For very porous surfaces:

1st coat: 75-150 sq. ft./gallon. **2nd coat** 250-400 sq. ft./gallon. **3rd coat** 500+ sq. ft./gallon.

For average density surfaces: 1st coat: 200-300 sq. ft./gallon. **2nd coat** 400-500 sq. ft./gallon.

For very dense surfaces: 1.5x avg. density coverage.

Generally, the sealer will go twice as far on the 2nd coat as it did on the 1st coat.

SURFACE PREPARATION

Always be sure surface is clean, dry, and free from any dirt, grease, oil, wax, or other contaminant. Read the entire label before using. Use only as directed. Always test on a small piece of material or a small inconspicuous area to determine suitability. Ensure the area is well ventilated. Ideal surface temperature should be between 60°F and 80°F. Product works best when it is the first substance applied to the surface, insuring proper penetration.

APPLICATION

NEW INSTALLATIONS- BEFORE & AFTER GROUTING: Apply with a solvent resistant paint roller having a 1/4 to 3/8-inch nap. Saturate paint roller and remove excess to prevent dripping. Apply one medium/heavy coat before grouting after tiles have been laid in place and set firmly. Roll on sealer liberally, evenly, smoothly, and uniformly. Do not leave voids and puddles. Work in small areas at a time. Let the sealer dry 12-24 hours before grouting. Clean grout and let surface dry 3-4 days to make sure the grout joints are dry before applying a second coat of sealer. Allow second coat to dry a minimum of 12 hours before applying a third coat if necessary. Gloss will increase as additional coats are added.

PACKAGING

1 qt: 12 units per case (30lbs)
1 gallon, 6 units per case (54lbs)
5 gallon, (42lbs)
55 gallon, (540lbs)

TRANSPORTATION

UN number: UN1139
UN proper shipping name: Coating Solution
Transport hazard class: 3
Packing group: 3

MANUFACTURER

Catalina Chemical Co.
4709 N. Lois Ave. Tampa, FL 33614

TECHNICAL SUPPORT

Support is available by calling (813) 876-5914
Emergency Support: ChemTel: 1(800) 255-3924

STORAGE AND HANDLING

CAUTION: Highly flammable & combustible liquid and vapor. Do not handle until all safety precautions have been read and understood.

Handling: Do not get in eyes, on skin, or on clothing. Do not breathe vapors or mists. Keep container closed and tightly sealed when not in use. Keep away from sources of ignition - No smoking. Take measures to prevent the buildup of electrostatic charge.

Conditions for safe storage: Keep in tightly closed, properly labeled containers. Keep in a cool, well-ventilated place.

Materials to avoid: Do not store with the following product types: Strong oxidizing agents, Explosives, Gases.

FIRST AID MEASURES

Eye Contact: Flush eyes with water. Seek medical attention if irritation persists.

Skin Contact: Remove contaminated clothing. Wash with soap and water. Seek medical attention if irritation persists.

Inhalation: If inhaled, remove to fresh air. If respiratory irritation, dizziness, nausea, or unconsciousness occurs, seek immediate medical assistance. In case of unconsciousness place patient stably in side position for transportation.

Ingestion: Do NOT induce vomiting unless directed to do so by medical personnel. Never give anything by mouth to an unconscious person. Rinse mouth with water. Seek medical attention if symptoms appear.